

# EN 197-1:2000

Table 1- The 27 products in the family of common cements

Main types	Notation of the 27 products (types of common cement)	Composition [proportion by mass <sup>1)</sup> ]											
		Main constituents								Limestone*			Minor additional constituents
		Clinker K	Blastfurnace slag S	Silica fume D <sup>2)</sup>	Pozzolana natural P	natural calcined Q	Fly ash siliceous V	Fly ash calcareous W	Burnt shale T	Limestone* L	Limestone* LL		
CEM I	Portland cement	CEM I	95-100	-	-	-	-	-	-	-	-	0-5	
	Portland-slag cement	CEM II/A-S	80-94	6-20	-	-	-	-	-	-	-	0-5	
		CEM II/B-S	65-79	21-35	-	-	-	-	-	-	-	0-5	
	Portland-silica fume cement	CEM II/A-D	90-94	-	6-10	-	-	-	-	-	-	0-5	
	Portland-pozzolana cement	CEM II/A-P	80-94	-	-	6-20	-	-	-	-	-	0-5	
		CEM II/B-P	65-79	-	-	21-35	-	-	-	-	-	0-5	
		CEM II/A-Q	80-94	-	-	-	6-20	-	-	-	-	0-5	
		CEM II/B-Q	65-79	-	-	-	21-35	-	-	-	-	0-5	
CEM II	Portland-fly ash cement	CEM II/A-V	80-94	-	-	-	-	6-20	-	-	-	0-5	
		CEM II/B-V	65-79	-	-	-	-	21-35	-	-	-	0-5	
		CEM II/A-W	80-94	-	-	-	-	-	6-20	-	-	0-5	
		CEM II/B-W	65-79	-	-	-	-	-	21-35	-	-	0-5	
	Portland-burnt shale cement	CEM II/A-T	80-94	-	-	-	-	-	6-20	-	-	0-5	
		CEM II/B-T	65-79	-	-	-	-	-	21-35	-	-	0-5	
	Portland-limestone cement	CEM II/A-L	80-94	-	-	-	-	-	-	6-20	-	0-5	
		CEM II/B-L	65-79	-	-	-	-	-	-	21-35	-	0-5	
		CEM II/A-LL	80-94	-	-	-	-	-	-	-	6-20	0-5	
		CEM II/B-LL	65-79	-	-	-	-	-	-	-	21-35	0-5	
	Portland-composite cement <sup>3)</sup>	CEM II/A-M	80-94	<----- 6-20 ----->								0-5	
		CEM II/B-M	65-79	<----- 21-35 ----->								0-5	
CEM III	Blastfurnace cement	CEM III/A	35-64	36-65	-	-	-	-	-	-	-	0-5	
		CEM III/B	20-34	66-80	-	-	-	-	-	-	-	0-5	
		CEM III/C	5-19	81-95	-	-	-	-	-	-	-	0-5	
CEM IV	Pozzolanic cement <sup>3)</sup>	CEM IV/A	65-89	-	<----- 11-35 ----->						-	0-5	
		CEM IV/B	45-64	-	<----- 36-55 ----->						-	0-5	
CEM V	Composite cement <sup>3)</sup>	CEM V/A	40-64	18-30	-	<----- 18-30 ----->			-	-	-	0-5	
		CEM V/B	20-38	31-50	-	<----- 31-50 ----->			-	-	-	0-5	

1) The values in the table refer to the sum of the main and minor additional constituents. 2) The proportion of silica fume is limited to 10%.

3) In Portland-composite cements CEM II/A-M and CEM II/B-M, in Pozzolanic cements CEM IV/A and CEM IV/B

and in Composite cements CEM V/A and CEM V/B the main constituents besides clinker shall be declared by designation of the cement.

\* L : total organic carbon (TOC) shall not exceed 0.5% by mass; LL: TOC shall not exceed 0.20% by mass.